

GASKETSEAL

Revision: 1/04/2024

Page 1 of 2

Technical Data

Basis	Polysiloxane
Consistency	Stable Paste
Curing System	Moisture Curing
Density (g/ml)	Ca. 1.27
Skin formation time* (23 °C/50% R.H) (min)	Ca. 14
Curing Speed *(23 °C/50% R.H) (mm/24hours)	Ca. 2
Slump (mm)	Non Sag
Hardness**, Shore A, Points (ISO 868)	Ca. 30 ± 5
Tensile Strength (N/mm ² (ISO 37)**	Ca. 2.50
Elongation at break (ISO 37)** (%)	± 500
Elastical Modulus 100% (ISO 37)** (N/mm ²)	Ca. 0.80
Temperature Resistance (°C)	-60→285
Application Temperature (°C)	5→35

*These values may vary depending on environmental factors such as temperature, moisture and the type of substrate.

**This information relates to fully cured products.

Description:

Gasketseal is a temperature resistant, elastic, one-component silicone sealant and replaces all cork, felt, fiber, paper and rubber gaskets in all thicknesses and widths.

Properties:

- Excellent resistance to fuels, oils and grease
- High temperature resistance
- Very easy to apply
- Permanently elastic after curing
- Typical acetic smell

Packaging:

Colour: red
Packaging: 310 ml cartridge

Applications:

- Formation of gasket and sealing rings
- Sealing between metal components
- Sealing of heating installations

Shelf Life and Storage:

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

Chemical Resistance:

Good resistance to water, aliphatic solvents, mineral oils, grease, diluted inorganic acids and alkalis. Poor resistance to aromatic solvents, concentrated acids and chlorinated hydrocarbons.

Health and Safety Recommendations:

Take the usual labour hygiene into account.
Consult label and material safety data sheet for more information.
Dangerous. Respect the precautions for use.

Substrates:

Substrates: Metals
Nature: Rigid, clean, dry, free of dust and grease.
Surface preparation: Prepare non-porous surfaces with a Soudal activator or cleaner (see Technical Data Sheet).
We recommend a preliminary adhesion and compatibility test on every surface. Not suitable for PE, PP, PTFE (eg. Teflon) and bituminous substrates.

GASKETSEAL

Revision: 1/04/2024**Page 2 of 2****Joint Size:**

Minimum Width: 5mm

Maximum Width: 30mm

Minimum Depth: 5mm

Recommendation: 2 x depth = width

Application Method:

Method: With a manual, pneumatic or caulking gun.

Cleaning: Clean with Soudal Surface Cleaner or with Soudal Swipex, immediately after use

Finishing: With a soapy solution or Soudal Finishing Solution before skinning.

Repair: With the same material.

Remarks:

- Because of the acid nature, certain metals (eg copper, lead) can be affected.
- Do not use in applications where continuous water immersion is possible.
- Not suitable for bonding aquariums.
- Gasketseal can not be used as a glazing sealant.
- Contact with bitumen, tar or other plasticizer releasing materials such as EPDM, neoprene, butyl, etc. is to be avoided since it can give rise to discolouration and loss of adhesion.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.
- Do not use on natural stones like marble, granite,...(staining).

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.