

SEALANT REMOVER

Revision: 1/04/2024

Page 1 from 1

Technical data

Basis	Based on hydrocarbons
Consistency	Liquid
Density	Ca. 0,87 g/ml
Viscosity	1400 +/- 600 Poise
Solubility in water	Not soluble
Solubility in other	Soluble in hydrocarbons
Application temperature	5 °C → 30 °C

* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Description:

Sealant Remover is a ready to use and rapid spray based on hydrocarbons for removing cured silicone and ms polymers.

Properties:

- Fast acting
- Does not drip
- Specifically for silicones and MS polymers

Applications:

- Removal of old silicone residue, spilled silicone or spilled MS polymeres from different kind of surfaces.
- Removes all residue of spilled silicone.

Packaging:

Colour: yellow-transparent

Packaging: 400 ml aerosol

Shelf life and Storage:

3 years in unopened packaging in a dry and cool environment at temperatures between +5°C and +25°C.

Substrates:

Substrates: coated metals, ceramic tiles, laminated plate, painted surfaces, glass, aluminium, some synthetic materials (NOT nylon and PMMA)

Nature: dry

Application Method:

Application method: Apply on dry ground and dry conditions. Remove hard putty first with a knife. Shake the canister thoroughly and apply Sealant Remover on the surface to be cleaned. Leave to work for at least 10 min. Wipe dry with a clean cloth. Repeat if necessary. Wash thoroughly with water to avoid surface degradation.

Health and Safety Recommendations:

Use only in well-ventilated areas. In case of contact with eyes, wash immediately with plenty of water. Always wear gloves and goggles. In case of contact with skin, wash with water and soap. Dangerous! Respect the precautions for use.

Remarks:

- Sealant Remover can cause staining on porous surfaces.
- Due to the wide variety of possible plastics and paints and to avoid damage to the surface, a preliminary compatibility test is recommended.

Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

Soudal India Pvt. Ltd.

Plot No. 200, Sec. 4, Phase - II, Growth Centre, Bawal, Dist. Rewari, Haryana - 123501 (India)

info@soudal.in | www.soudal.in | +91 8010-114-114