

## Soudafoam FR HY

Revision: 03/04/2023

Page 1 of 2

### Technical Data

Basis	Polyurethane
Consistency	Stable foam, thixotropic
Curing System	Moisture curing
Specific Gravity (kg/m <sup>3</sup> )	Ca. 40
Skin formation time (23°C/50% R.H.) (min)*	9.5
Cutting time (EN 17333-3) (min)*	50
Tensile Strength (EN 17333-4)(kPa)**	Ca. 134
Elongation at Fmax (EN 17333-4) (%)**	Ca. 14.2
Shear strength (EN 17333-4) (kPa)	Ca. 59
Compressive strength (EN 17333-4) (kPa)	Ca. 70
Expansion after curing (EN 17333-2) (%)	<1
Shrinkage after curing (EN 17333-2) (%)	<1
Joint Yield (EN 17333-1)	750 ml yields ca. 34 l of foam
Box Yield (EN 17333-1)	750 ml yields ca. 18 m of foam
Sound insulation (EN ISO 717-1) (dB)	60
Thermal conductivity (λ) (EN 12667) (W/m.K)	0.033
Temperature Resistance (°C)**	-40 to +90 (cured)

\*These values may vary depending on environmental factors such as temperature, moisture and the type of substrate.

\*\*This information relates to fully cured products.

### Product description

Soudafoam FR HY is a one-component, selfexpanding, ready to use PU-foam, which contains HCFC- and CFC-free propellants who are not harmful for the ozonlayer. Soudafoam FR HY is a PU-foam with fire retardant characteristics according to the European standard EN 1366-4.

- As part of the 'Soudal Fire Range' assortment for penetration seals and joints.
- Sealing of all openings in roof constructions.
- Apply of an acoustic baffle
- All foam applications in static joints.

### Properties

- Fire resistant in a joint (EN 1366-4) for 240 minutes
- High filling capacity
- Good adhesion on all surfaces (except PE, PP and PTFE).
- High insulation value, thermal and acoustic
- Very good bonding properties.
- Water resistant (not watertight)
- Not UV-resistant

### Applications

- Installation of fireproof doors and windows.
- Sealing of fire retardant joints in walls and ceiling.

### Packaging

Colour: pink

Packaging: 750 ml aerosol (net)

### Shelf life

15 months unopened and stored in dry and cool conditions (Between 5 and 25 °C), Upright storage is recommended.

**Remark:** The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

## Soudafoam FR HY

Revision: 03/04/2023

Page 2 of 2

### Health- and Safety Recommendations

Take the usual labour hygiene into account. Always wear gloves and goggles. Remove cured foam mechanically. Never burn away. Consult label and material safety data sheet for more information. When vaporizing (for example with a compressor), additional security measures will be required. Use only in well ventilated areas.

### Application method

Shake the aerosol can for at least 20 seconds. Put the adapter on the valve. Moisten surfaces with a water sprayer prior to application. For non-conventional substrates a preliminary adhesion test is recommended. Remove pressure from the applicator to stop. Fill holes and cavities for 1/3, as the foam will expand. Repeat shaking regularly during application. If you have to work in layers repeat moistening after each layer. Fresh foam can be removed using Soudal Gun & Foamcleaner or acetone. Prior to using the Gun & Foamcleaner, test whether surfaces are affected or not. Especially plastics and lacquer or paint layers can be sensitive to this. Cured foam can only be removed mechanically or with Soudal PURemover.

Can temperature: +5 °C - 30 °C

Ambient temperature: +5 °C - 30 °C.

Surface temperature: +5 °C - 35 °C

### Standards and certificates

- Tested according to standard EN 1366-4 for fire-resistant jointing
- Classification report according to EN 13501-2 by Warrington Exova (report nr. 19660B) and in combination with fire-resistant sealants (19660C)
- EMICODE EC1 Plus - Lizenz 11728 (GEV, Düsseldorf)
- M1 Emission classification of building materials
- Sound insulation (EN ISO 717-1) - Test report 20-002317-PR01 PB 01-K05-04-en-03 (IFT Rosenheim)

**Remark:** The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

**McCoy Soudal Sealants Adhesives & Foams Pvt. Ltd.**

Unit No. 505 B, Tower B, 5th Floor, BPTP Park Centra, Sector-30, NH-8, Gurugram, Haryana - 122002 (India)  
info@soudal.in | www.soudal.in | +91 8010-114-114