

SOUDASEAL FR

Revision: 1/04/2024

Page 1 of 2

Technical Data

Basis	SMX polymer
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (23°C/50% R.H.)	Ca. 10 min
Curing speed * (23°C/50% R.H.)	Ca. 2 mm/24h
Hardness**	33 ± 5 Shore A
Density	1,57 g/ml
Elastic recovery (ISO 7389)**	> 70 %
Maximum allowed distortion	± 25 %
Max. tension (ISO 37)**	0,82 N/mm ²
Elasticity modulus 100% (ISO 37)**	0,33 N/mm ²
Elongation at break (ISO 37)**	430 %
Temperature resistance**	-40 °C - 90 °C
Application temperature	1 °C - 30 °C
Fire resistance (EN 13501-2) **	≤ 240 min

*These values may vary depending on environmental factors such as temperature, moisture and the type of substrate.

**This information relates to fully cured products.

Description:

Soudaseal FR is a high-quality, fire-resistant, smoke-tight, neutral, elastic, one-component joint and adhesive sealant based on SMX-Polymer (Hybrid).

Properties:

- High level of fire retardation
- Permanently elastic after curing (without fire load)
- Outstanding bond strength on nearly all surfaces, even on slightly wet surfaces
- Very good mechanical characteristics
- Easy to use and apply, also under difficult circumstances.
- Colourfast and UV resistant
- Paintable
- No bubble formation within sealant (in high temperature and humidity applications)
- Does not contain isocyanates, solvents or halogens

Packaging:

Colour: grey

Packaging: 600 ml foil bag, other packaging on request

Applications:

- Fire retardant expansion and connection joints in the construction industry
- Sealing of fire-retardant joints in prefab buildings and sky scrapers
- Flexible connections in automotive applications
- As part of the Soudal Fire Range assortment for penetration seals and joints.

Shelf Life and Storage:

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Chemical Resistance:

Good resistance to water, aliphatic solvents, mineral oils, grease, diluted inorganic acids and alkalis. Poor resistance to aromatic solvents, concentrated acids and chlorinated hydrocarbons.

Health and Safety Recommendations:

Take the usual labour hygiene into account.

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

Soudal India Pvt. Ltd.

Plot No. 200, Sec. 4, Phase - II, Growth Centre, Bawal, Dist. Rewari, Haryana - 123501 (India)

info@soudal.in | www.soudal.in | +91 8010-114-114

SOUDASEAL FR

Revision: 1/04/2024

Page 2 of 2

Consult label and material safety data sheet for more information.

Dangerous! Respect the precautions for use.

Substrates:

Substrates: all usual building substrates, treated wood, PVC, plastics

Nature: rigid, clean, dry, free of dust and grease.

Surface preparation: Porous surfaces should be treated with Soudal Primer 150. All smooth surfaces can be treated with Soudal Surface Activator. A preliminary adhesion test on every surface is recommended.

Joint Dimensions:

Consult the 'Fire Range Installation Instructions Openings and Sealing' on the Soudal website for the correct joint dimensions depending on the required fire resistance.

Application Method:

Method: With manual or pneumatic caulking gun.

Cleaning: Clean with White Spirit or Soudal Surface Cleaner immediately after use (before curing). Or with Soudal Swipex.

Finishing: With a soapy solution or Soudal Finishing Solution before skinning.

Repair: With the same material.

Remarks:

- Soudaseal FR may be overpainted with water based paints, however due to the large number of paints and varnishes available we strongly suggest a compatibility test before application.
- The drying time of alkyd resin based paints may increase.
- Soudaseal FR can not be used as a glazing sealant.

Standards and Certificates:

- European Technical Approval Soudaseal FR-ETA 13/0334.
- CE-marked (BCCA - EC conformity CPR).
- Joint Sound Reduction Test by IFT.
- Various test and classification reports in various accredited testing institutes: IFT Rosenheim, ITB Poland, Warrington Fire Gent, Warrington Fire Australia, Efectis Netherlands, Efectis France, CSTB France, CSI Italy.
- Test results for penetration seals and / or joints with Soudaseal FR are freely accessible in the 'Fire Range Application manual Penetration seals and Joints' on the Soudal Website. The corresponding certificates can be obtained through the Soudal sales representatives or through the Soudal Website.

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

Soudal India Pvt. Ltd.

Plot No. 200, Sec. 4, Phase - II, Growth Centre, Bawal, Dist. Rewari, Haryana - 123501 (India)

info@soudal.in | www.soudal.in | +91 8010-114-114