



Acryrub Exterior

Description

Acryrub Exterior is a high-quality, plasto-elastic, one-component joint sealant based on siliconized acrylic dispersions.

Properties

- Suitable for interior & exterior applications
- Excellent crack bridging properties
- Good adhesion to most of the substrates including uPVC, aluminium, wood, metals, concrete, steel and masonries
- Good movement capability
- Good UV resistance
- Colorfast and waterproof after curing

Applications

- Sealing compound for cracks in concrete and plaster.
- Connection joints in the building industry.
- Joints between windowsills (uPVC, aluminum & wood), between skirting board and floor, between brickwork, etc.
- Perimeter sealing around windows, doors, and other building components to prevent air, water and dust infiltration.
- Joints with movement upto $\pm 15\%$.



Technical Data

Base	Acrylic Dispersion
Consistency	Paste
Curing system	Physical Drying
Specific Gravity (g/ml)	1.5
Skin formation (minutes)	ca. 20
Shrinkage (%)	DIN 52451 ≤ 15
Maximum allowed joint movement (%)	± 15
Temperature Resistance ($^{\circ}\text{C}$)	-20 to +80
Application Temperature ($^{\circ}\text{C}$)	+5 to +30

Footnote: Skinning time and curing speed may vary depending on environmental factors such as temperature, moisture, and type of substrates

Substrates

- Substrate condition
The surface must be rigid, clean, dry, free of dust and grease.
- Substrate preparation
Highly porous surfaces should be primed with diluted Acryrub Exterior (1 part Acryrub Exterior + 2 parts water).
- Substrate types
Acryrub Exterior has a good adhesion to all common porous building substrates.
Acryrub Exterior has no good adhesion or is not suitable for PE, PP, PTFE (Teflon®), bituminous substrates, copper or copper containing materials such as bronze and brass.

We recommend a preliminary adhesion test on every surface.



Acryrub Exterior

Application method

- Application method
Apply the product with a manual, pneumatic or a battery-operated caulking gun.
- Cleaning method
Before curing, Acryrub Exterior can be removed with water from substrates and tools. Cured sealant must be removed mechanically.
- Finishing method
Finish with a spatula or putty knife.
- Repair method
Repair with the same material.

Joint Size

Minimum Width: 5 mm
Maximum Width: 20 mm
Minimum Depth: 5 mm
Recommendation for sealing jobs: Joint Depth = Joint Width

Use PE backer rods in case of large joint dimensions to avoid three-point adhesion.

Health and Safety Recommendations

Take the usual labour hygiene into account. Consult the packaging label and safety data sheet for more information.
Dangerous. Respect the precautions for use.

Packaging/Logistics

Colour: White
Packaging: 425g Cartridge, 425g Sausage
Shelf life: 12 months from the date of production. The product must be stored in its original, undamaged, and sealed packaging under dry conditions, protected from direct sunlight, and at temperatures between +5°C and +25°C.

Remarks

- Do not use in applications where continuous water immersion is possible.
- Paintable with most paints, however given the great diversity in available paints, it is recommended to do a compatibility test prior to the application.
- Do not apply when rain or frost is imminent.
- The paint should be sufficiently elastic to be applied on a plasto-elastic sealant. A preliminary test is recommended to prevent cracking.

This technical data sheet supersedes all earlier versions. The information provided is based on our tests and practical experience and is supplied in good faith as general guidance only, without creating any liability. Since materials, substrates, application design, and processing conditions vary widely and are outside our control, we cannot accept responsibility for the results obtained from use of this information. The user must verify suitability for the intended application through their own testing, and preliminary trials are recommended in all cases. The manufacturer reserves the right to change product specifications without prior notice.