

Soudabond Easy Genius

Revision: 1/04/2024

Page 1 of 5

Technical Data

Base	Single component polyurethane
Consistency	Stable adhesive foam (does not sag)
Curing system	Moisture cure at room temperature
Skin formation (*)	About 8 minutes - 30 mm adhesive bead
Can be trimmed (!)	About 60 minutes - 30 mm adhesive bead
Full strength (*)	About 12 hours - 30 mm adhesive bead
Post expansion	Minimal
Thermal conductivity (DIN 52612)	About 0.036 W/m.K
Tensile strength (DIN EN 1607)	0,19 N/mm ²
Shear strength (DIN EN 12090)	0,142 N/mm ²
Shear modulus (DIN EN 12090)	0,489 N/mm ²
Temperature resistance	-40°C to +90°C +120°C (up to max. 1 hour)
Reaction to fire classification (EN 13501-1)	No classification (F)

*These values may vary depending on environmental factors such as temperature, moisture and the type of substrate.

**This information relates to fully cured products.

Description:

Soudabond Easy Genius is a ready to use, single-component, self-expanding polyurethane adhesive for clean, efficient, and economical permanent bonding of insulation panels and plasterboard in building and construction.

Properties:

- Cuts working time by up to 30%
- Excellent initial bond, even at low temperatures
- Economical in use due to precise application
- One can covers up to 12 m² of insulation
- Suitable for vertical applications
- Can be applied at temperatures between -5°C and +35°C
- Thermal conductivity 0.036 W/m.K enhances performance of insulation panels when filling gaps
- Remains flexible, does not become brittle
- Levels uneven surfaces
- Limited post expansion for fast and precise installation of insulation panels and plasterboard
- Substantial space and weight savings compared to conventional PU roof adhesives, bonding mortars, etc.
- Fast curing, work can continue about 1 hour after application

- Solvent-free
- Resistant to a variety of solvents, paints and chemicals
- Does not age or rot, mold and mildew resistant, but not UV resistant
- Water resistant (not watertight)

Packaging:

Colour: Orange
Packaging: 750 ml aerosol can (12 per box)

Applications:

- Clean, efficient, and economical permanent bonding of insulation panels
- Suitable for bonding polystyrene (EPS + XPS), polyurethane (PUR/PIR), and phenol resin foam based insulation panels for flat roofs, perimeters, facades, insulation/drain elements, cellar ceilings, internal insulation, etc.
- Suitable for bonding gypsum plasterboard/gypsum fiberboard in dry lining applications
- Suitable for bonding non-load bearing walls, e.g., partition walls, screen walls, cellar bars, stone shelves, etc., of concrete precision blocks (aerated concrete, sand-lime brick, gypsum, hollow bricks...)

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

Soudal India Pvt. Ltd.

Plot No. 200, Sec. 4, Phase - II, Growth Centre, Bawal, Dist. Rewari, Haryana - 123501 (India)
info@soudal.in | www.soudal.in | +91 8010-114-114

SOUDABOND EASY GENIUS

Revision: 1/04/2024

Page 2 of 5

- Fills cavities between individual thermal insulation panels

Shelf Life and Storage:

18 months from the date of production in unopened packaging with cool (+5°C to +25°C) and dry storage. Cans must be stored upright to prevent blockage of spray valve. Once opened, keep the container tightly closed and use within a short period.

Substrates:

All usual substrates such as concrete, masonry, stone, plaster, wood, cold bituminous thick coatings, sand or slate surfaced bituminous sheeting, polystyrene, polyurethane, and phenol resin foam, corrosion-protected steel sheeting, fiber cement, gas concrete, particleboard, plasterboard, gypsum fiberboard, fiber cement, hard PVC, and emulsion paints.

Adhesive surfaces must be stable, clean, without bubbles, and free of separating agents such as talcum, grease, oils, etc. Suitable are building moist, but not wet (water film, standing water) substrates. Any cement slurries and sinter layers on mineral substrates must be removed mechanically. Bubbles in bituminous sheeting must be removed. To ensure perfect adhesion, the bituminous sheeting should have a fully covered surface. Does not adhere to PE, PP, PTFE, and silicone.

All substrates should be tested for suitability with regard to adhesion and compatibility.

Directions for Use:

General: Prior to using the product, cover all adjacent areas for protection against soiling. In windy conditions, precautions must be taken to ensure that SOUDABOND EASY GENIUS cannot contaminate components, objects, or persons in the vicinity.

Good ventilation must be ensured for indoor use. Wear protective goggles and gloves. Shake the aerosol can for at least 20 seconds. Open the cover and fold the tube horizontally. After extended periods of non use, the can must be shaken again to obtain the required adhesive quality! Adjust the adhesive bead to the required diameter by pushing on the genius gun harder or softer. (The emptier the can, the more force should be set). The can must be held vertical during application.

A distance of 1 to 2 cm must be maintained between the nozzle and insulation panel/substrate while spraying.

Apply pressure to the insulation panel within about 8 minutes (20°C-65% R.H. – this time is shorter at higher temperature/humidity and longer at lower temperature/humidity). Do not tap or remove and reapply panels as this will damage the adhesive structure and reduce the adhesive strength substantially. At high temperatures and low humidity in particular, curing can be accelerated by lightly spraying the adhesive bead with water.

When finished, wait approximately 1 minute until the foam stops dripping out. Detach the butterfly plug from the cap and screw it on top of the red Soudamax adapter. Clip cap back in place to lock trigger.

Instructions for re-use:

Before reusing, unscrew the red Soudamax adapter from the tip of the straw. Keep the can straight up, point the straw into a plastic bag and shoot the contents of the straw into it. It may take one or two triggers to remove all the straw's contents. Screw the Soudamax adapter back into the straw. Then unscrew the red T-plug from the red Soudamax adapter at the end of the straw to start working.

1. Bonding Flat Roof Insulation Materials:

Apply SOUDABOND EASY GENIUS directly to the substrate. Pressure should be applied to the insulation panels for optimal contact and maintained using suitable weights for at least 15 minutes to prevent lifting and slipping through wind suction. The panels must not be subjected to traffic for about 2 hours. Consumption: At least three uniform adhesive beads with a minimum diameter of 30 mm are required per sqm adhesive surface. The number of adhesive strips, according to DIN 1055, part 4, depends on the region, roof area, structure height, corner and edge areas as well as the materials to be bonded. The amount of adhesive to be applied depends on the wind load and must be increased in corner and edge areas.

2. Perimeter Insulation:

SOUDABOND EASY GENIUS facilitates the installation of insulation panels in perimeter areas according to DIN 4108-2. (Not suitable for pressing water!). Spray SOUDABOND EASY GENIUS from bottom to top with a bead spacing of about 25 cm (minimum three beads per continuous panel or minimum two beads for short panels!) onto the insulation panel or cellar wall. Press the

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

SODABOND EASY GENIUS

Revision: 1/04/2024

Page 3 of 5


insulation panel lightly against the cellar wall. Work from bottom to top without gap. The insulation panels must be bonded staggered in corners of buildings. The installed insulation panels can be readjusted with a long spirit level to correct any post-expansion of the adhesive within 8 minutes. The insulation achieves its final strength through the pressure of the filled soil, gravel, or similar. Filling must take place within 14 days after bonding.

3. Facade/Wall Insulation:

In Germany, according to ETAG Directive 004, exterior thermal insulation composite systems with rendering require building inspectorate approval for the entire thermal insulation composite system, including approval of the utilized adhesive by the German Institute for Building Technology (DIBt). In this area requiring approval, the system provider with appropriate system approval should be contacted directly!

In all other cases, SODABOND EASY GENIUS is ideal for bonding insulation panels to interior walls and exterior facades!

The can must be held vertical during application. Apply a circular bead of SODABOND EASY GENIUS to the insulation panel with enclosed M/W to cover an adhesive area of minimum 40% with pressure applied.



Wait at least 2 to maximum 8 minutes (20°C/65% R.H. – this time is shorter at higher temperature/humidity and longer at lower temperature/humidity) and subsequently press the insulation panel against the wall. Work from bottom to top without gap. Insulation panels must be bonded staggered in outer corners of buildings. Installed insulation panels can be adjusted with a long spirit level after 10 to 15 minutes to correct any post-expansion of the adhesive. It is recommended to fix the last installed insulation panel during breaks.

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

4. Cellar Ceiling Insulation:

For working overhead, suitable protective goggles must be worn!

SODABOND EASY GENIUS has a very high initial bonding strength and is therefore ideal for permanent bonding of insulation panels to cellar ceilings, garage ceilings, or other overhead areas, also without additional mechanical fastening. Suitable are all standard insulation panels of polystyrene (EPS and XPS) and PUR/PIR measuring 500 x 500 mm with a maximum thickness of 100 mm and a maximum weight of 400 g. Larger and heavier insulation panels and/or additional surfaces should be fixed mechanically within 15 minutes. This is easily done using ceiling supports, for example. Prior to application, the substrate stability must be verified. This can also take place with a sealing tape test.

In this test, sealing tape is applied to the substrate and quickly pulled off again. If old paint or plaster adheres to the adhesive tape, this means that the substrate does not have the necessary stability and must be reinforced or removed. With chalking and highly absorbent substrates, the substrate adhesion can be improved with a deep solvent primer. Protruding concrete burrs must be removed mechanically.

At least one circular and one angular adhesive foam bead with a minimum diameter of 30 mm (about 40 g per panel) must be applied to each 500 x 500 mm panel. Do not apply the adhesive too close to the outer edges to avoid the excess going over the edges when pressure is applied to the insulation panel. **Before bonding the insulation panel to the ceiling, SODABOND EASY GENIUS must be allowed to stand for 3 to maximum 6 minutes to achieve the required initial strength.**

The insulation panel can subsequently be bonded to the ceiling. The panel must be placed carefully in the required position and pressure applied without tapping (damages the adhesive structure). **The next insulation panel must be bonded 5 minutes after the previously bonded panel so that it remains in place when the next panel is bonded.** Insulation panels must be additionally fixed in the center with a suitable insulation anchor under unfavorable bonding conditions.

5. Interior Insulation/Dry Lining:

Prior to application, the substrate stability must be

Soudabond Easy Genius

Revision: 1/04/2024

Page 4 of 5

verified. This can also take place with a sealing tape test. In this test, sealing tape is applied to the substrate and quickly pulled off again. If old paint or plaster adheres to the adhesive tape, this means that the substrate does not have the necessary stability and must be reinforced or removed. With chalking and highly absorbent substrates, the substrate adhesion can be improved with a deep solvent primer. Remove protruding concrete burrs or excess plaster. SOUDABOND EASY GENIUS levels uneven surfaces up to 30 mm.

Interior Insulation Panels:

Apply SOUDABOND EASY GENIUS about 2 cm away from the edge of the panel as a 30 mm circular bead and to the panel surface in lines or a W-shape. It must be ensured that the adhesive contact area is about 40% after applying pressure. The adhesive must always be applied circular also for panel cut-outs, penetrations, etc., to prevent rear circulation of the interior insulation. After applying SOUDABOND EASY GENIUS, depending on the climatic conditions, allow to flash off for about 3-6 minutes. This ensures that an optimal adhesive strength is achieved with reduced post-expansion. Subsequently place the insulation panel on wedges, align and apply pressure from bottom to top. Do not tap or remove the panels as this can reduce the adhesive strength substantially. Apply new adhesive if necessary. After about 6 to 10 minutes, check for correct seating, readjust with a spirit level/level. Edges of walls, ceilings, and floors, openings, and penetrations must be filled out completely with SOUDABOND EASY GENIUS air-tight and sound insulated. Work can be continued after a minimum of 1 hour. SOUDABOND EASY GENIUS can also be used for mounting electrical installation boxes.

Plasterboard: In contrast to interior installation, three vertical adhesive beads are sufficient for the installation of plasterboard wider than 50cm. For panel widths below 50cm, a minimum of two adhesive beads must be applied.

6. Concrete Precision Block Bonding:

SOUDABOND EASY GENIUS must not be used for components requiring approval, e.g., supporting walls and walls relevant for safety!

Good ventilation must be ensured for indoor use!
Clean the adhesive surfaces, remove loose particles and

moisten. Apply two SOUDABOND EASY GENIUS adhesive beads with a diameter of about 30mm to the substrate and subsequently to all further concrete precision blocks. The adhesive beads must be applied about 50 mm away from the stone edge parallel on horizontal and vertical joints. Position/join and align bricks within a minimum of 2 to maximum of 8 minutes (20°C/65% R.H. – this time is shorter at higher temperature/humidity and longer at lower temperature/humidity). If once joined bricks are removed, new adhesive beads must be applied. Allow excess adhesive to cure and subsequently remove, e.g., with a spatula. Depending on the ambient temperature, work can be continued after a minimum of 60 minutes. The adhesive achieves full strength after a minimum of 12 hours.

7. Other Applications:

Due to its excellent adhesive properties, reduced foaming, and fast final strength, SOUDABOND EASY GENIUS is suitable for numerous bonding applications. SOUDABOND EASY GENIUS is ideal for the installation of insulation panels in building and construction. Installation of loft insulation reveals and claddings as well as bonding of wall edging strips are just a few examples.

General Note: Do not load/subject the bond to traffic within the curing time of about 2 hours! All open joints within the insulation can be filled out with SOUDABOND EASY GENIUS. Trim protruding, fully cured adhesive with a sharp knife. SOUDABOND EASY GENIUS can be painted or plastered after curing.

Application temperature:

+5°C to +35°C (adhesive surface temperature)
+5°C to +25°C (can temperature) – optimal +15 to +25°C. If required, slowly bring the can to the optimal temperature by placing in cool or warm water.

Cleaning: with GUN & FOAM CLEANER or SWIPEX prior to curing, subsequently with PU REMOVER or remove mechanically.

Repair option: with SOUDABOND EASY GENIUS.

Safety Recommendations:

Observe the standard industrial hygiene procedures. Wear protective goggles and gloves. Remove cured adhesive mechanically, never remove with a flame. Use only in well-ventilated areas. For further information on

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

SOUDABOND EASY GENIUS

Revision: 1/04/2024

Page 5 of 5

product safety and handling, refer to the information on the container.

Environmental Clauses:

Leed regulation:

Soudabond Easy Genius conforms to the requirements of LEED. Low – Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Meets USGBC LEED requirements v4.1: Low-Emitting Materials - Adhesives & Sealants regarding VOC content.

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

Soudal India Pvt. Ltd.

Plot No. 200, Sec. 4, Phase - II, Growth Centre, Bawal, Dist. Rewari, Haryana - 123501 (India)
info@soudal.in | www.soudal.in | +91 8010-114-114