



Soudafoam FR HY Gun

Product description

Soudafoam FR HY Gun is a one-component, moisture-curing, self-expanding, ready to use polyurethane foam. The canister is provided with a thread so it can be used on a gun. Soudafoam FR HY Gun is fire resistant according to EN 1366-4. Because of the Duravalve, the optimal yield remains over the entire shelf life, even when stored or transported lying down.

Properties

- Fire resistant in a joint (EN 1366-4) for 240 minutes
- As part of the 'Soudal Fire Range' assortment for penetration seals and joints
- High filling capacity
- Good adhesion on all surfaces (except PE, PP and PTFE)
- High insulation value, thermal and acoustic
- Very good bonding properties
- Not UV-resistant
- Very precise to dose



Applications

- Installation of fireproof doors and windows.
- Sealing of fire resistant joints in walls and ceiling.
- Filling of cavities.
- Sealing of all openings in roof constructions.
- Apply of an acoustic baffle.
- All foam applications in static and not static joints.
- Filling and insulating around pipes and electrical wiring.

Technical data

Base		Polyurethane
Consistency		Stable foam, thixotropic
Curing system		Moisture curing
Skin formation	EN 17333-3	7 minutes
Cutting time	EN 17333-3	20 minutes
Thermal conductivity (λ)	EN 12667	0,034 W/m.K
Sound insulation	EN ISO 717-1	60 dB
Density	EN 17333-1	ca. 19 kg/m³
Joint yield	EN 17333-1	750 ml yields ca. 35 m of foam
Box yield	EN 17333-1	750 ml yields ca. 44 l of foam
Shrinkage after curing	EN 17333-2	< 2%
Expansion after curing	EN 17333-2	< 2%
Compression strength	EN 17333-4	ca. 30 kPa
Shear strength	EN 17333-4	ca. 48 kPa
Tensile strength	EN 17333-4	ca. 93 kPa



MFPA Leipzig GmbH
Gesellschaft für Materialforschung und
Prüfungsanstalt für das Bauwesen Leipzig mbH



Soudafoam FR HY Gun

Elongation at Fmax	EN 17333-4	ca. 12%
Temperature resistance	-40°C → +90°C	

Footnote: Skinning time and curing speed may vary depending on environmental factors such as temperature, moisture, and type of substrates.

Application method

- Application method
Shake the aerosol can for at least 20 seconds. Fit the gun on the adapter. Surface should be free from grease and dust. Moisten surfaces with a water sprayer prior to application. For non-conventional substrates a preliminary adhesion test is recommended. Fill holes and cavities for 2/3, as the foam will expand. Repeat shaking regularly during application. If you have to work in layers repeat moistening after each layer. Fresh foam can be removed using Soudal Gun & Foamcleaner. Prior to using the Gun & Foamcleaner, test whether surfaces are affected or not. Especially plastics and lacquer or paint layers can be sensitive to this. Cured foam can only be removed mechanically or with Soudal PU-Remover.
- Can temperature
+5 °C to +30 °C
- Ambient temperature
+5 °C to +35 °C
- Surface temperature
+5 °C to +35 °C

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult the packaging label and safety data sheet for more information.
Always wear gloves and goggles.
Remove cured foam mechanically. Never burn away.
When vaporizing (for example with a compressor), additional security measures will be required.
Use only in well-ventilated areas.

Packaging/Logistics

Colour: Pink
Packaging: 750 ml aerosol (net)
Shelf life: 15 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C

Standards and certificates

- Tested according to standard EN 1366-4 for fire-resistant jointing
- Classification report according to EN 13501-2 by Warrington Exova (report nr. 19660B) and in combination with fire-resistant sealants (19660C)
- EC1 Plus label: very low emission
- M1 Emission classification of building materials
- Sound insulation (EN ISO 717-1)
- Thermal conductivity (EN 12667)

Remarks

- Moisten surfaces with a water sprayer prior to application.
- If you have to work in layers repeat moistening after each layer.
- For not common surfaces we recommend an adhesion test.
- Not UV-resistant, cured polyurethane foam must be protected against UV exposure by overpainting, sealing with sealants (e.g. silicones, polyurethane, acrylic or hybrid polymer) or covering.

Soudafoam FR HY Gun

This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. It is general in nature and does not constitute any liability. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application. In every case it is recommended to carry out preliminary experiments. The manufacturer reserves the right to modify products without prior notice.